



BROOKSIDE LABORATORIES, INC.
GEOTECHNICAL DIVISION
200 WHITE MOUNTAIN DRIVE
NEW BREMEN, OH 45869

**** PHYSICAL ANALYSIS REPORT ****

Dragon Ridge C.C.
Henderson, NV

File Number: 47746

Date Received/Started : 4/10/2023
Date Completed/Reported: 4/18/2023
Date Issued: 4/18/2023

Submitted By: Soil and Water Consulting

Lab Number	0769
Sample Description	WCS&G 90/10 QC #1
Sample Condition	<u>XX</u> Normal ___ Other (see comments)

Method References

ASTM D5550
ASTM F1632
ASTM F1647 - Method A
ASTM F1815

D Values

** D10: 0.25
** D60: 0.67
** Coefficient of Uniformity: 2.68

*Reported values are an average of duplicated analysis

** NON A2LA ACCREDITED
* *This report may only be reproduced in its entirety.*
* *These results represent the sample submitted only.*



Geotechnical
(Putting Green Materials)
Certificate Number: 736.01

CAPPING CHARACTERISTICS

Dragon Ridge C.C.
Henderson, NV

File Number : 47746
** Date of Analysis **
Start Date : 4/10/2023
Completed : 4/18/2023

Submitted By: Soil and Water Consulting Reviewed by:

Lab Number 0769
Sample Description WCS&G
90/10
QC #1

Particle Size Analysis

Clay	<.002mm	%	1.0
Silt	.002mm - .05mm	%	1.4
Sand	.05mm - 2.00mm	%	97.6
Gravel	> 2.0mm	%	0.0

Org Mat 360 deg C (LOI) 0.56

Sand Fractions

Sieve Size		% Retained
#	mm	
10 -	2.0	Fine Gravel 0.0
18 -	1.0	Very Coarse Sand 7.3
35 -	.500	Coarse Sand 49.0
60 -	.250	Medium Sand 33.6
100 -	.150	Fine Sand 6.3
140 -	.106	Very Fine Sand 1.1
270 -	.053	Very Fine Sand 0.3

Soil Moisture Measurements

Saturated Conductivity in/hr 10.6

Soil Density

Bulk Density	g/cc	1.57
Particle Density	g/cc	2.65


MOISTURE RETENTION %**PORE SPACE %**

		TOTAL	CAPILLARY	AIR FILLED
SATURATION	22.2	40.8	40.8	0.0
10 CM	18.0	40.8	28.3	12.4
20 CM	16.2	40.8	25.4	15.3
30 CM	10.1	40.8	15.8	24.9
40 CM	8.2	40.8	12.9	27.9

File Number: 47746
 Client Name: Dragon Ridge C.C.
 Submitted By: Soil and Water Consulting
 Start Date: 4/10/2023
 Completed: 4/18/2023

Lab Number: 0769
 Sample Description: WCS&G
 90/10
 QC #1

Pore Spaces



Moisture Retention

