



BROOKSIDE LABORATORIES, INC.
GEOTECHNICAL DIVISION
200 WHITE MOUNTAIN DRIVE
NEW BREMEN, OH 45869

**** PHYSICAL ANALYSIS REPORT ****

Freestone Club
Fairfield, TX

File Number: 91984

Date Received/Started : 5/20/2024
Date Completed/Reported: 5/21/2024
Date Issued: 5/21/2024

Submitted By: Soil and Water Consulting

Lab Number	1296
Sample Description	HOLSEY PEA GRAVEL
Sample Condition	☐ Normal ☒ Other (see comments)

Method References

ASTM C136

D Values

** D15: 5.67
** D90: 10.58
** Coefficient of Uniformity: 1.87

*Gravel Sample
*Less than 2,000 grams of sample

** NON A2LA ACCREDITED
* *This report may only be reproduced in its entirety.*
* *These results represent the sample submitted only.*



Geotechnical
(Putting Green Materials)
Certificate Number: 736.01

**** PHYSICAL ANALYSIS REPORT ****

Freestone Club
Fairfield, TX

File Number : 91984
** Date of Analysis **
Start Date : 5/20/2024
Completed : 5/21/2024

Submitted By: Soil and Water Consulting Reviewed by:

Lab Number	1296
Sample Description	HOLSEY
	PEA
	GRAVEL

GRAVEL FRACTIONS	% Retained
Sieve Size (mm)	

12.5	0.0
9.5	15.6
6.35	61.5
4.75	18.5
2.36	3.6
2.0	0.1
1.0	0.2
< 1.0	0.5