




BROOKSIDE LABORATORIES, INC.
GEOTECHNICAL DIVISION
200 WHITE MOUNTAIN DRIVE
NEW BREMEN, OH 45869

**** PHYSICAL ANALYSIS REPORT ****

Porter Valley Country Club
19216 Singing Hills Drive
Northridge, CA 91326

File Number: 91413

Date Received/Started : 5/1/2025
Date Completed/Reported: 5/7/2025
Date Issued: 5/7/2025

Submitted By: Soil and Water Consulting

Lab Number	0998
Sample Description	GILLIBRAND 30 SAND
Sample Condition	<u>XX</u> Normal ___ Other (see comments)

Method References

ASTM F1632
ASTM F1647 - Method A

D Values

** D10: 0.28
** D60: 0.50
** Coefficient of Uniformity: 1.76

*Reported values are an average of duplicated analysis

** NON A2LA ACCREDITED
* *This report may only be reproduced in its entirety.*
* *These results represent the sample submitted only.*



Geotechnical
(Putting Green Materials)
Certificate Number: 736.01

**** PHYSICAL ANALYSIS REPORT ****

Porter Valley Country Club
19216 Singing Hills Drive
Northridge, CA 91326

File Number : 91413
** Date of Analysis **
Start Date : 5/1/2025
Completed : 5/7/2025

Submitted By: Soil and Water Consulting Reviewed by:

Tiffany Albers

Lab Number 0998
Sample Description GILLIBRAND
30 SAND

Particle Size Analysis

Clay	<.002mm	%	0.3
Silt	.002mm - .05mm	%	0.4
Sand	.05mm - 2.00mm	%	99.3
Gravel	> 2.0mm	%	0.0

Org Mat 360 deg C (LOI) 0.10

Sand Fractions

Sieve Size			% Retained
#	mm		
10 -	2.0	Fine Gravel	0.0
18 -	1.0	Very Coarse Sand	0.0
35 -	.500	Coarse Sand	39.0
60 -	.250	Medium Sand	58.4
100 -	.150	Fine Sand	1.6
140 -	.106	Very Fine Sand	0.2
270 -	.053	Very Fine Sand	0.1
